



## TYPICAL PHYSICAL PROPERTIES

*Kushon*<sup>®</sup> Sponge

**#4130**

Color	Tan
Polymer	Natural Rubber
Compression Deflection at 25% Compression	Medium Firm (10-16 psi)
Compression Set 50% Deflection at 158°F	15% Maximum
Accelerated Aging % Change in Compression Deflection at 158°F	+/- 20%
Temperature Range	-20°F to 160°F
Density-Average	30 pcf

**NOTE:** Information of a technical nature is based on laboratory tests which either Griswold conducts or sends to an independent laboratory for testing for determination of uses as requested in writing by customer. Griswold believes these to be reliable. However, Griswold has no control over the application of the material to or part of the final PRODUCT and THEREFORE, Griswold makes NO EXPRESS OR IMPLIED WARRANTY OF RESULT, FITNESS OR MERCHANTABILITY. The customer should determine reliability for the end use or particular application.