



TYPICAL PHYSICAL PROPERTIES

enlighten- microcellular polyurethane

#U7E26

Color Standard	Black (0426)
Thickness Specification	+/- 10%
Density Nominal	26 pcf
Compression Deflection at 25% compression	15 +/- 20% psi
Compression Set at 50% compression, 23°C	<2%
at 50% compression, 70°C	<8%
Autoclave then 50% compression, 70°C	<5%
Tensile Strength	>85 psi
Elongation	>90%
Tear Strength	>9 pli
Service Temperatures Continuous Use Range	-40°C to 70°C

NOTE: Information of a technical nature is based on laboratory tests which either Griswold conducts or sends to an independent laboratory for testing for determination of uses as requested in writing by customer. Griswold believes these to be reliable. However, Griswold has no control over the application of the material to or part of the final PRODUCT and THEREFORE, Griswold makes NO EXPRESS OR IMPLIED WARRANTY OF RESULT, FITNESS OR MERCHANTABILITY. The customer should determine reliability for the end use or particular application.